



Specification

Clear Tank Liner

Property	Specification	Tolerance	Test Method
Thickness	1.65mm	+/- 5%	Micrometer (after embossing)
Width	48"~60"	-0, +1/2"	Off roll, relaxed
Specific Gravity	1.30	+/- 0.02	D792
Durometer Hardness	80	+/-4	Shore A
Tensile Strength	2300 / 2100 psi	Minimum	D882
100% Modulus	1200 / 1000 psi	Minimum	D882
Elongation	300 / 300%	Minimum	D882
Tear Strength	450 / 450 lbf/in	Minimum	D1004
Dimensional Stability	-4.0 / +1.0%	Maximum	D1204, @70°C
Water Extraction	0.20%	Maximum	D1239
Volatile Loss	0.60%	Maximum	D1203
Cold Crack Resistance	-30°C	Pass	D1790
Operating Temperature	80°C	Nominal	Conditioning

Brochure disclaimer: All the test values are based on an average data in our lab and are believed to be true and accurate to the best of our knowledge.

This information does not constitute a warranty or guarantee, it will not relieve the user from the responsibility of the proper and safe use of the product.